## SHANGHAI WALLIS TECHNOLOGY CO.,LTD

## GENERAL INDUSTRY LIMITED

## PVC film for pharmaceutical

## **Examination Report**

(	Commodity P			VC FILM Dimensions		0.25mmX275mm	
LC	LOT. Number WLS2			20250627-1 Standard		YBB00212005-2015	
D	Date of MFG 2			025.7.6 Date of EXP		2028.7.5	
				Test Item a	and Conclusion		
Item				Requirements		Test Result	Conclusion
Appearance			nce	Free from colour difference, wrinkles, dirt, foreign particles, perforation, fisheye's diameter		Yes	Qualified
	≥300			±2 mm			
width			<300		±1 mm	275	Qualified
Thickness			ess	±0.02mm		0.24-0.26	Qualified
Density				$1.35{\sim}1.45$ g/cm $^3$		1.36	Qualified
Water Vapour Transmission				≤2.5g/(m²·24h)		0.8	Qualified
Oxygen Transmission				≤30cm³/(m²·24h·0.1MPa)		7.9	Qualified
Tensile Strength				TD:≥44MPa		62.3	Qualified
				MD:≥44MPa		60.3	Qualified
Falling Ball Impact Breakage Rate  Heat Shrinking rate				TD:≤40%		0	Qualified
				MD:≤40%		0	Qualified
				TD:≤±6.0%		+0.8	Qualified
				MD: ≤±6.0%		-1.7	Qualified
Heat Sealing Strength				≥7.0 N/15mm		17.6	Qualified
Vinyl Chloride Monomer				≤0.0001%		<0.0001%	Qualified
Carbon Particles				≤10 Particles/m² melt		≤10	Qualified
Test of Extraction	Degree of Clear			Ought to be clear		Clear	Qualified
	Easily Oxidized Substances			Difference of titrant consumed by test solution and blank solution should be ≤1.5 ml		0.9	Qualified
	Heavy Metal		≤0.0001%		<0.0001%	Qualified	
	Non-		Water	≤30mg/100ml		1.7	Qualified
	Vola	tile	Ethanol	≤30mg/100ml		1.4	Qualified
	substa	ance	n-Hexane	≤30mg/100ml		2.0	Qualified
	Barium		Ought to be clear		Yes	Qualified	
Microbial Limit Test		Bacteria		≤1000/100cm²		Not found	Qualified
		Mold & Yeast		≤100/100cm <sup>2</sup>		Not found	Qualified
LIIIII	LIESL	E.Coli		Not allowed		Not found	Qualified
Approval				Check		For and on behalf of General Industry 通用工業有限 Test	公 司